

Établissement secondaire

SAS capital 220 465 €
RCS Bourg-en-Bresse 509386009
TVA FR57509386009
(T) +33 (0) 4 72 25 13 00
(F) +33 (0) 4 78 06 02 52

TECHNICAL SPECIFICATION - PENR24

<u>PROPERTIES</u>	<u>TEST METHOD</u>	<u>UNIT</u>	<u>VALUE</u>
Density	DIN 53420	kg/m ³	24
Tensile Strength	DIN 53571	N/mm ²	
Extrusion Direction			0.219
Cross Direction			0.170
Elongation at Break	DIN53571	%	
Extrusion Direction			67
Cross Direction			52
Compression Strength	DIN 53577	N/mm ²	
25 % (4 th compression)			0.024
50 % (4 th compression)			0.081
70 % (4 th compression)			0.200
Thermal Stability	ASTM D-3575-S	%	<3
(24h at 70° C)			
Cell Size	BS 4443/1 Met 4	Cells 25mm	± 21
Water Absorption	DIN 53428	Vol %	1.19
(After 24hours)			
Working Temp Range	Internal	° C	-30 : +80